



MALENA CERAMIC TILE



MALENA CERAMIC TILE



3" x 10" MALENA IVORY CERAMIC BULLNOSE
56-053



3" x 13" MALENA IVORY CERAMIC BULLNOSE
46-169



10" x 16" MALENA IVORY CERAMIC WALL TILE
56-052



13" x 13" MALENA IVORY CERAMIC FLOOR TILE
46-168



8" x 10" MALENA IVORY CERAMIC
WALL TILE 52-191



2" x 2" MALENA IVORY MOSAICS
46-172

MALENA CERAMIC TILE



3" x 10" MALENA ICE CERAMIC BULLNOSE
56-049



3" x 13" MALENA ICE CERAMIC BULLNOSE
46-165



10" x 16" MALENA ICE CERAMIC WALL TILE
56-048



13" x 13" MALENA ICE CERAMIC FLOOR TILE
46-164



8" x 10" MALENA ICE CERAMIC
WALL TILE 52-189



2" x 2" MALENA ICE MOSAICS
46-170

MALENA CERAMIC TILE



3" x 10" MALENA CARBON CERAMIC BULLNOSE
56-051



3" x 13" MALENA CARBON CERAMIC BULLNOSE
46-167



10" x 16" MALENA CARBON CERAMIC WALL TILE
56-050



13" x 13" MALENA CARBON CERAMIC FLOOR TILE
46-166



8" x 10" MALENA CARBON CERAMIC
WALL TILE 52-190



2" x 2" MALENA CARBON MOSAICS
46-171

MALENA CERAMIC TILE

PACKAGING INFORMATION

DESCRIPTION	ITEM CODE			LBS/BOX	PCS/BOX	SQFT/BOX	BOXES/SKID	SQFT/SKID
	IVORY	ICE	CARBON					
13" x 13" MALENA CERAMIC FLOOR TILE	46-168	46-164	46-166	44.24	11	12.91	58	748.90
8" x 10" MALENA CERAMIC WALL TILE	52-191	52-189	52-190	26.94	20	10.76	92	989.92
10" x 16" MALENA CERAMIC WALL TILE	56-052	56-048	56-050	42.00	14	15.06	48	723.07
2" x 2" MALENA MOSAICS	46-172	46-170	46-171	40.00	10	11.74	48	563.52
3" x 13" MALENA CERAMIC BULLNOSE	46-169	46-165	46-167	21.00	21	n/a	84	1764 pcs.
3" x 10" MALENA CERAMIC BULLNOSE	56-053	56-049	56-051	15.00	25	n/a	98	2450 pcs.

GENERAL SPECIFICATIONS

DESCRIPTION	METHOD	UNIT	13" x 13"
THICKNESS		mm – in	7.6 mm – 5/16"
WATER ABSORPTION	EN ISO 10545-3	(%)	≤ 3
ABRASION RESISTANCE	EN ISO 10545-7	(PEI)	4
SCRATCH HARDNESS		(Mohs)	6
BREAKING STRENGTH	EN ISO 10545-4	(lbf)	≥ 250
CHEMICAL RESISTANCE	EN ISO 10545-13	(GL)	Class A – Resistant
FROST RESISTANCE	EN ISO 10545-12		Resistant
STATIC COEFFICIENT OF FRICTION (WET)	ASTM C-1028	(μ)	< 0.60
STATIC COEFFICIENT OF FRICTION (DRY)	ASTM C-1028	(μ)	≥ 0.80
DCOF (WET)	ANSI B101.3		< 0.42
SHADE VARIATION			V2